



EAGLE ELASTOMER (EXTRUSION) FLUOROELASTOMER COMPOUNDS

I TYPICAL PHYSICALS I

COMPOUND NUMBER	POLYMER TYPE	COLOR	SHORE A DURO	SPECIFIC GRAVITY	TENSILE (PSI)	ELONGATION (%)	COMPRESSION SET (%)
EE77475H	EXTREME VITON® (ETP)	BLACK	78	1.88	2580	275	38.6
EE98476H	LOW TEMP VITON® (GFLT)	BLACK	78	1.87	2855	250	15.8
EE98380L	(70 % FLUORINE) VITON®	BLACK	79	1.9	2100	205	25
EE98178H	(70 % FLUORINE) VITON®	BLACK	76	1.92	3200	305	10.3
EE97376B	(68 % FLUORINE) VITON®	BLACK	77	1.87	2135	210	20.1
EE97371F	(68 % FLUORINE) VITON® (FDA)	WHITE	67	2.20	2005	385	14.8
EE97362B	(68 % FLUORINE) VITON®	BLACK	61	1.89	2100	355	16.5
EE97361B	(68 % FLUORINE) VITON® (FDA)	WHITE	62	2.03	2005	410	20.7
EE97360B	(66 % FLUORINE) VITON® (FDA)	BLACK	61	1.89	2100	355	19.4
EE96972B	(66 % FLUORINE) VITON®	WHITE	73	2.22	1890	260	14.8
EE96290B	(66 % FLUORINE) VITON®	BLACK	90	1.84	2290	115	12.2
EE96273R	(66 % FLUORINE) VITON®	GREEN	73	2.10	1755	225	11.1
EE96272B	(68 % FLUORINE) VITON® (FDA)	WHITE	73	2.22	1890	260	14.8
EE96174F	(66 % FLUORINE) VITON® (FDA)	BLACK	73	2.03	2055	210	15
EE96262B	(66 % FLUORINE) VITON® (FDA)	WHITE	59	1.91	1705	280	11.4
EE96255B	(66 % FLUORINE) VITON®	BLACK	56	1.84	1280	330	9.3
EE96175T	(66 % FLUORINE) VITON®	BLACK	76	1.88	2250	180	8.3
EE94475H	LOW TEMP VITON® (GLT)	BLACK	78	1.84	2930	260	9.3
EE96166B	(66 % FLUORINE) VITON®	BLACK	67	1.84	2200	245	6.9
EE96160B	(66 % FLUORINE) VITON®	BLACK	61	1.89	1710	245	7.6
EE66445A	(66 % FLUORINE) TECHNOFLON®	BLACK	49	1.84	855	370	16
EE56174B	(66 % FLUORINE) DYNEON™	BROWN	75	2.04	2250	150	8.5
EE30678A	FEPM AFLAS™	BLACK	78	1.62	2400	220	29.8

Viton® is a registered trademark of DuPont Performance Elastomers

Dyneon™ is a registered trademark of 3M.

Aflas™ is a registered trademark of Asahi Glass Company

Tecnoflon® is a registered trademark of Solvay Solexis

EAGLE ELASTOMER HAS MANY ADDITIONAL FKM COMPOUNDS TO MEET YOUR SPECIFIC NEEDS.

Published Date 09-2007

Expiration Date 09-2008

P.O. BOX 939 • CUYAHOGA FALLS, OH 44223-0939 • (330) 923-7070 • Fax (330) 923-4005

Website: www.eagleelastomer.com