



EAGLE ELASTOMER (QUICK TURN AROUND, STOCKED) FLUOROELASTOMER COMPOUNDS

*** 10 lb min purchase quantity***

For quantity price breaks and availability please call (330)923-7070.

TYPICAL PHYSICALS

COMPOUND NUMBER	COLOR	SHORE A DURO	SPECIFIC GRAVITY	TENSILE (PSI)	ELONGATION (%)	COMPRESSION SET (%)	10 LB PRICE PER LB	PROCESS
EE96255A (66 % FLUORINE) VITON®	BLACK	56	1.85	1230	330	10	\$22.81	Compression Transfer molding
EE96260A (66 % FLUORINE) VITON®	BLACK	62	1.85	1775	290	7.7	\$22.37	Compression Transfer molding
EE66445A (66 % FLUORINE) TECNOFLON®	BLACK	50	1.85	865	370	13	\$35.54	Compression Injection Transfer
EE96275A (66 % FLUORINE) VITON®	BLACK	76	1.86	2360	180	7	\$21.81	Compression Transfer molding
EE96290B (66 % FLUORINE) VITON®	BLACK	90	1.84	2290	115	12.2	\$19.24	Extruding Compression molding
EE98178H (70 % FLUORINE)* VITON®	BLACK	76	1.92	3200	305	10.3	\$27.32	Compression Injection Transfer
EE98380L (70 % FLUORINE) VITON®	BLACK	79	1.9	2100	220	25	\$23.01	Compression Injection Transfer
EE96174F (66 % FL. FDA) VITON®	BLACK	73	2.03	2055	210	15	\$22.35	Compression Injection Transfer
EE96272B (66 % FL. FDA) VITON®	WHITE	73	2.22	1890	260	14.8	\$20.95	Extruding Compression molding
EE96171R (66 % FLUORINE) VITON®	BROWN	72	2.04	2150	195	NA	\$17.93	Compression Transfer molding
EE97376A (68 % FLUORINE) VITON®	BLACK	76	1.88	2390	245	13.4	\$18.71	Compression Transfer molding
EE96273R (66 % FLUORINE) VITON®	GREEN	73	2.10	1755	225	N/A	\$20.85	Extruding Compression molding
EE94475H LOW TEMP * VITON® (GLT)	BLACK	78	1.84	2930	260	9.3	\$48.24	Compression Injection Transfer
EE98476H LOW TEMP * VITON® (GFLT)	BLACK	78	1.87	2855	250	15.8	\$49.71	Compression Injection Transfer
EE77475H EXTREME * VITON® (ETP)	BLACK	78	1.88	2580	275	N/A	\$195.62	Compression Injection Transfer
EE30678A FEPM * AFLAS®	BLACK	78	1.62	2400	220	N/A	\$25.53	Compression Transfer molding

*= PEROXIDE CURE

Viton® is a registered trademark of DuPont Performance Elastomers.

Dyneon® is a registered trademark of 3M.

Aflas® is a registered trademark of AGC

Tecnoflon ® is a registered trademark of Solvay Solexis.

EAGLE ELASTOMER HAS MANY ADDITIONAL FKM COMPOUNDS TO MEET YOUR SPECIFIC NEEDS.

Published Date 09-16-08

Expiration Date 12-31-09

P.O. BOX 939 • CUYAHOGA FALLS, OH 44223-0939 • (330) 923-7070 • Fax (330) 9234005

www.eagleelastomer.com